

# PRODUCT DATA SHEET

## Sikasil®-670 Fire

### FIRE RATED JOINT SEALANT



#### DESCRIPTION

Sikasil®-670 Fire is a fire rated, 1-component, moisture-curing, low-modulus elastic joint sealant.

#### USES

Sikasil®-670 Fire is designed for fire rated movement and connection joints on porous and non-porous substrates.

#### CHARACTERISTICS / ADVANTAGES

- Up to 4 hours fire resistance according to EN 1366-4
- Very good resistance to weathering
- Movement capability of  $\pm 35\%$  (ASTM C 719)
- Easy to smooth and very good workability
- Good adhesion to many different substrates
- Neutral curing

#### SUSTAINABILITY

- EMICODE EC1 PLUS R
- LEED v4 EQc 2: Low-Emitting Materials

#### APPROVALS / CERTIFICATES

- EN 15651-1 F EXT-INT CC 25 LM
- EN 15651-4 PW INT
- ISO 11600 F 25 LM & G 25 LM
- ASTM C 920, class 35
- EN 1366-4 assessment report
- ETA (ETAG 026)
- UL listing (UL 2079)
- EN 13501-2 classification report
- EN 140-3

#### PRODUCT INFORMATION

<b>Composition</b>	Neutral cure silicone
<b>Packaging</b>	600 ml foil pack, 20 foil packs per box 300 ml cartridge, 12 cartridges per box
<b>Colour</b>	White, grey, black
<b>Shelf life</b>	Sikasil®-670 Fire has a shelf life of 12 months from the date of production, if it is stored in undamaged, original, sealed packaging, and if the storage conditions are met.
<b>Storage conditions</b>	Sikasil®-670 Fire shall be stored in dry conditions, where it is protected from direct sunlight and at temperatures between +5 °C and +25 °C.
<b>Density</b>	~1.35 kg/l (ISO 1183-1)

#### TECHNICAL INFORMATION

<b>Shore A Hardness</b>	~16 (after 28 d) (ISO 868)
-------------------------	----------------------------

<b>Secant Tensile Modulus</b>	~0.30 N/mm <sup>2</sup> at 100 % elongation (23 °C) ~0.50 N/mm <sup>2</sup> at 100 % elongation (-20 °C)	(ISO 8339)
<b>Elongation at Break</b>	~650 %	(ISO 37)
<b>Elastic Recovery</b>	~70 %	(ISO 7389)
<b>Tear Propagation Resistance</b>	~4.0 N/mm	(ISO 34)
<b>Movement Capability</b>	±25 % ±35 %	(ISO 9047) (ASTM C 719)
<b>Service Temperature</b>	-40 °C min. / +150 °C max.	

#### Joint Design

The joint width must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be ≥ 10 mm and ≤ 40 mm. The joint depth shall be ≤ 20 mm. A width to depth ratio of 2:1 must be maintained (for exceptions, see table below).

#### Standard joint widths for joints between concrete elements:

Joint distance [m]	Min. joint width [mm]	Min. joint depth [mm]
2	10	10
4	15	10
6	20	10
8	30	15
10	35	17

All joints must be correctly designed and dimensioned in accordance with the relevant standards, before their construction. The basis for calculation of the necessary joint widths are the type of structure and its dimensions, the technical values of the adjacent building materials and the joint sealing material, as well as the specific exposure of the building and the joints.

For larger joints please contact our Sika Technical Service.

## APPLICATION INFORMATION

Consumption	Joint width [mm]	Joint depth [mm]	Joint length [m] per 600 ml foil pack
	10	10	6
	15	10	4
	20	10	3
	25	12	2
	30	15	1.3

<b>Backing Material</b>	Use polyethylene foam backing rods.		
<b>Sag Flow</b>	~2 mm (20 mm profile, 50 °C)	(ISO 7390)	
<b>Ambient Air Temperature</b>	+5 °C min. / +40 °C max.		
<b>Substrate Temperature</b>	+5 °C min. / +40 °C max., min. 3 °C above dew point temperature		
<b>Curing Rate</b>	~2 mm/24 hours (23 °C / 50 % r.h.)	(CQP 049-2)	
<b>Skinning time</b>	~25 min (23 °C / 50 % r.h.)	(CQP 019-1)	
<b>Tooling Time</b>	~20 min (23 °C / 50 % r.h.)	(CQP 019-2)	

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Sikasil®-670 Fire adheres without primers and/or activators

### APPLICATION METHOD / TOOLS

Sikasil®-670 Fire is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a foil pack or cartridge into the sealant gun and extrude Sikasil®-670 Fire into the joint making sure that it comes into full contact

with the sides of the joint and avoids any air entrapment. Sikasil®-670 Fire sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Do not use tooling products containing solvents.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically. For cleaning skin use Sika® Cleaning Wipes-100.

### FURTHER INFORMATION

- Safety Data Sheet (SDS)
- EN 13501-2 classification report
- ETAG 026 assessment report
- Brochure Sika Fire Protection Solutions

### IMPORTANT CONSIDERATIONS


- Sikasil®-670 Fire cannot be overpainted.
- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Do not use Sikasil®-670 Fire on natural stone.
- Do not use Sikasil®-670 Fire on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use Sikasil®-670 Fire to seal joints in and around swimming pools.
- Do not use Sikasil®-670 Fire for joints under water pressure or for permanent water immersion.
- Do not expose uncured Sikasil®-670 Fire to alcohol containing products as this may interfere with the curing reaction.

### BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### Sika Italia S.p.A.

Via Luigi Einaudi, 6  
20068 Peschiera Borromeo (MI)  
Phone: +39 02 54778 111  
Fax: +39 02 54778 119  
info@sika.it  
www.sika.it



Product Data Sheet  
Sikasil®-670 Fire  
August 2017, Version 03.01  
020515030000000012

### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sikasil-670Fire-en-IT-(08-2017)-3-1.pdf